


KS608A TECHNICAL DATA















MATERIAL OVERVIEW

KS608A is a high tough SLA resin for accurate and durable parts, which has all the benefits and convenience associated with KS408A but is significantly stronger and resist to higher temperature. KS608A is in light yellow color. It's applicable for a wide range of applications, ideal for functional prototypes, concept models and low volume production parts in the field of automotive, architecture and consumer electronics industries.

ADVANTAGES

- High strength and strong toughness
- Accurate and dimensionally stable
- Excellent temperature resistance
- Good moisture resistance

IDEAL APPLICATIONS

- Functional model need to be tough
- Conceptual model
- Low volume production models
- Automotive, aerospace, architecture, electronic applications

TECHNICAL DATASHEET

| liquid properties | | o | Optical Properties | |
|-------------------|------------------------|--------------------------|--------------------|--|
| Appearance | Light yellow | Dp | 0.135-0.155 mm | |
| Viscosity | 355-455 cDs 0, 28 °C | Ec | 9-12 mJ/em | |
| Density | 1.11-1.14g/em3 @ 25 °C | Building layer thickness | 0.05-0.15mm | |

| Mechanical Properties | | UV Posture |
|-----------------------------------|-------------------|-------------|
| MEASUREMENT | TEST METHOD | VALUE |
| Hardness, Shore D | ASTM D 2240 | 76-82 |
| Flexural modulus, Mpa | ASTM D 790 | 2.650-2.760 |
| Flexural strength, Mpa | ASTM D 790 | 65- 74 |
| Tensile modulus. MPa | ASTM D 638 | 2,160-2,360 |
| Tensile strength, MPa | ASTM D 638 | 25-30 |
| Elongation at break | ASTM D 638 | 12-20% |
| Impact strength, notched lod, J/m | ASTM D 256 | 58 - 70 |
| Heat deflection temperature. C | ASTM D 648 @66PSI | 58-68 |
| Glass transition, Tg, C | DMA, E'peak | 55-70 |
| Density, g/cm3 | | 1.14-1.16 |